

Color Filter and Method for Fabricating the Same

Field of the Invention

The present invention relates to color filters pass bands that change with spatial
5 location on the filter.

Background of the invention

The present invention may be more easily understood in the context of a camera that
10 utilizes a color sensitive array of photodiodes to record an image. To provide color
sensitivity, the photodiodes are typically divided into three classes of photodiodes that detect,
respectively, red, green, and blue light. The various color sensitive photodiodes are dispersed
over the array. For example, the detector array may consist of an array of pixels in which
each pixel includes three photodiodes, one for measuring red light, one for measuring green
15 light, and one for measuring blue light.

The color sensitive detectors are typically constructed by constructing transmission
filters that select particular color pass bands over an array of identical photodiodes. That is,
the camera chip can be viewed as an array of more or less color insensitive photodetectors
20 covered with a filter having pass bands that vary with spatial position on the filter. The filters
are typically constructed from a pigment filter that is deposited over a photodiode that is
sensitive to light over a broad spectral range that includes red, blue, and green. For example,
a color camera array can be fabricated by using conventional photolithography techniques to
pattern either a red, blue, or green filter over each of the photodiodes in the array by
25 selectively depositing the pigment in question. However, this process is limited by the
materials that can be used for the pigment filter. Therefore, only limited color filter profiles
can be created. For example, these filters are unable to block infrared (IR) light, and hence,
such camera modules have to incorporate an additional IR blocking filter that significantly
increases the costs of the camera.

30 In addition, providing a particular predetermined color profile is difficult. In general,
the designer must use one or more filters whose transmission curves are not within the control
of the designer. For example, the filter profiles obtained with the pigment filters do not

match the standard filter profiles used to specify the color that will be perceived by a human observer at each pixel. Consider an application in which the color of a light source is to be reproduced on a printer for viewing by a human observer. While the light source may have a very complex spectrum, the eye perceives the source as having a single color that can be replicated by combining light from three colored sources. The printer is calibrated using some standardized color system such as the CIE 1931 standard. Given RGB values representing the intensity of light having the RGB spectral patterns in the standard system, the printer will produce the correct color. That is, a human observer will perceive the paper as having the same color as the light source even though the spectrum of light leaving the paper is different from that of the light.

The RGB values measured by the sensor using the pigment filters measure the intensity of light in a weighted wavelength band determined by the pigment filter transmission curve. Denote the measured intensities from the pigment filter light detectors by $R'G'B'$. In general, these $R'G'B'$ values differ from the RGB values that would be obtained by an ideal filter for the standard, since filter weighting functions are different. Hence, if these pigment-based values are sent to the printer, the printer will generate a color that is different from that of the light that was input to the color sensor.

Filters having more desirable color profiles can be fabricated by using interference techniques; however, these filters are difficult to construct over small area photodiodes. Hence, these filters are not useful for color cameras and the like in which very small pixel dimensions are needed. Interference filters are constructed by depositing multiple thin film layers of transparent dielectrics of different refractive indexes. The wavelength and filter profile are set by varying the thickness and index of refraction for the dielectrics. This provides great flexibility in the filter profile design. However, this technique is not suitable for CCD camera chips since it is difficult to pattern the individual pixels for high-resolution cameras. Hence, for a camera to utilize interference filters three separate arrays on three separate chips are required. Each chip detects an image for light of one color. The three monochrome images would then be combined to provide the final color image. Since each chip requires only one type of filter that covers the entire chip, the problems associated with fabricating small individual photodiode-sized filters are eliminated. However, the need for three separate camera chips increases the cost and complexity of the camera optical system.

In addition, the intensity of light available to each chip is reduced by a factor of three, which increases the amount of light needed to make a color measurement.

Summary of the Invention

5 The present invention includes a color filter and method for fabricating the same. The color filter has a primary filter layer and a first trim filter. The primary filter layer is partially transparent to light, the primary filter layer having a transmission function as a function of wavelength. The transmission function also varies as a function of the spatial location on the
10 primary filter layer, The primary filter transmits light in a first band of wavelengths about a first characteristic wavelength at a first location in the primary filter layer and transmits light in a second band of wavelengths about a second characteristic wavelength at a second location in the primary filter layer. The first trim filter includes a layer of material that overlies the first and second locations and that preferentially attenuates light at a first trim
15 wavelength between the first and second characteristic wavelengths. The first trim filter has a transmission function as a function of wavelength that is substantially the same at the first and second locations. In one embodiment, the first trim filter further preferentially attenuates light at a second trim wavelength. In this embodiment, the first trim wavelength is less than one of the first and second characteristic wavelengths and the second trim wavelength is
20 greater than that characteristic wavelength. In one embodiment, the first trim filter includes an interference filter. In one embodiment, the primary filter layer includes a first dye filter located at the first location and a second dye filter located at the second location. In one embodiment, the color filter further includes a second trim filter. The second trim filter includes a layer of material that preferentially attenuates light at a second wavelength that is
25 different from each of the characteristic wavelengths and the first trim wavelength. In one embodiment, the dye filters are located between the first and second trim filters.

Brief Description of the Drawings

30 Figure 1 illustrates how the color transmission curve, as a function of wavelength that is obtained with a typical red pigment filter, differs from that of the color profile for the CIE 1931 red color profile

Figure 2 compares the color transmission curve as a function of wavelength that is obtained with a typical green pigment filter and the color profile for the CIE 1931 green color profile.

5

Figure 3 compares the color transmission curve as a function of wavelength that is obtained with a typical blue pigment filter and the color profile for the CIE 1931 blue color profile.

10 Figure 4 is a cross-sectional view of a color sensor that utilizes a filter according to one embodiment of the present invention.

Figure 5 compares the transmission curves of some typical pigment filters.

15 Figure 6 illustrates the response curves for the photodiodes underlying filters according to one embodiment of the present invention.

Figures 7-9 are cross-sectional views through a portion of a color sensor array using a filter according to another embodiment of the present invention at various stages in the
20 fabrication process

Figure 10 is a cross-sectional view of another embodiment of a color sensor that utilizes a filter according to the present invention.

25 **Detailed Description of Preferred Embodiments of the Invention**

The present invention may be more easily understood with reference to a color system based on the CIE 1931 color standard. However, as will be discussed in more detail below, the principles of the present invention can be applied to other color systems. Refer now to
30 Figure 1, which illustrates how the color transmission curve, as a function of wavelength that is obtained with a typical red pigment filter, differs from that of the color profile for the CIE 1931 red color profile. The pigment profile is shown at 10 and the CIE 1931 standard profile

is shown at 11. As can be seen from the drawing, the color profile of the pigment filter extends significantly beyond that of the CIE 1931 standard. Similarly, the color transmission curves of the typically used pigment filters for green and blue are also much broader than the corresponding filter profiles in the CIE 1931 standard as can be seen from Figures 2 and 3.

Figure 2 compares the color transmission curve as a function of wavelength that is obtained with a typical green pigment filter and the color profile for the CIE 1931 green color profile. The pigment profile is shown at 20, and the CIE 1931 standard profile is shown at 21. Figure 3 compares the color transmission curve as a function of wavelength that is obtained with a typical blue pigment filter and the color profile for the CIE 1931 blue color profile. The pigment profile is shown at 30 and the CIE 1931 standard profile is shown at 31.

The present invention is based on the observation that an improved set of color filters can be obtained by combining the pigment filters described above with a second filter that selectively blocks light in the regions of the spectrum in which the pigment filters transmit more light than a filter designed to have the corresponding standard profile. The pigment filters vary from location to location on the filter, while the second filter has a transmission function that does not substantially vary over the filter. Referring again to Figure 1, it can be seen that the red pigment filter transmits more light in the region of the spectrum shown at 12 than a filter that provides the standard profile shown at 11. The present invention utilizes band-blocking filters to remove this excess transmitted light. Denote the transmission of the red pigment filter by $TPR(\lambda)$ and that of a filter providing the standard filter profile by $TSR(\lambda)$. For the purposes of this discussion, these filters will be assumed to provide the same maximum transmissions. In this case, the ideal band-blocking filter has a transmission given by

$$TBR(\lambda) = TSR(\lambda) / TPR(\lambda) \quad (1)$$

Analogous band-blocking filters can be provided for the other pigment filters to tailor the resultant compound filter to be closer to that of the desired standard filter. The pigment-based filters tend to have much broader transmission curves than the more ideal standard transmission curves for the corresponding colors. For example, the locations of the bands to be blocked in the transmission curve of the blue filter are shown at 32 and 33 in Figure 3. In general, there are one or two bands in the pigment filter transmission curves that must be

attenuated to convert the pigment filter transmission curve into a transmission curve that is more nearly that of the desired transmission curve.

To simplify the following discussion, the pigment filters discussed above will be referred to as the primary spatially varying filters and the band blocking filters will be referred to as the common spectral trim filters. The present invention utilizes the observation that the common spectral trim filters can be combined into a single compound filter that has transmission minima at each of the bands to be blocked. The manner in which such a filter is constructed will be discussed in more detail below. For the purposes of the present discussion, it is sufficient to note that each common spectral trim filter ideally has essentially 100 percent transmission in the spectral regions that are separated from the band that is blocked by the filter. Hence, if a plurality of such filters are stacked, the transmission in the spectral regions between the blocked bands is essentially unchanged. Accordingly, a single compound filter comprising a stack of such trim filters can be placed over or under the red, blue, and green pigment filters. As a result, trim filters having physical dimensions that are much wider than a single pigment filter can be utilized, and hence, the size limitations discussed above are less critical. In fact, a single compound trim filter can be placed over or under the entire array of color sensors as a single layer that needs little if any geometric patterning.

Refer now to Figure 4, which is a cross-sectional view of a color sensor that utilizes a filter according to one embodiment of the present invention. Color sensor 50 includes three photodetectors 51-53. Each photodetector is covered by a corresponding pigment filter. The filters corresponding to photodetectors 51-53 are shown at 61-63, respectively. A compound trim filter 70 is used to "trim" the transmission curves of the pigment filters in a manner similar to that described above. Trim filter 70 is preferably placed between the photodetectors and the pigment filters; however, embodiments in which the trim filter is placed over the pigment filters can also be constructed.

The transmission curves of some typical pigment filters and trim filters are shown in Figure 5. The normalized transmission curve for the trim filter is shown at 70, and the normalized transmission curves for the red, blue, and green pigment filters are shown at 71-73, respectively. The response curves for the photodiodes underlying the filters that detect

red, blue and green light are shown at 81-83, respectively in Figure 6. For the purposes of this discussion, a pigment filter will be defined to be any filter that alters the color spectrum of light passing therethrough by preferentially absorbing light of a particular wavelength to induce a transition between two atomic or molecular energy states in the filter material.

- 5 Pigment filters that can be patterned using conventional lithography are available from Fuji Films.

The manner in which the trim filter is constructed will now be discussed in more detail. The preferred band-blocking filter is an interference filter constructed from a plurality
10 of transparent layers of a uniform thickness in which adjacent layers have different indices of refraction. This type of filter is well known in the art, and hence, will not be discussed in detail here. For the purposes of this discussion, it is sufficient to note that a stack of such layers will block light of a wavelength determined by the thickness and indices of refraction of the layers. Light of other wavelengths is not blocked, and hence, passes through the layer
15 stack with little attenuation. Hence, a number of such filters can be stacked to provide a compound filter that blocks light at each wavelength in a predetermined set of wavelengths while transmitting light at wavelengths that are not in the predetermined set.

Refer now to Figures 7-9, which are cross-sectional views through a portion of a color
20 sensor array 100 using a filter according to another embodiment of the present invention at various stages in the fabrication process. Referring to Figure 7, the process starts with a substrate 101 having a plurality of photodiodes constructed therein. Exemplary sets of photodiodes are shown at 102 and 110. Each set of photodiodes includes 3 separate photodiodes as shown at 111-113.

25

Referring now to Figure 8, substrate 101 is placed in a deposition chamber and the various layers in the compound interference filter are deposited on the surface of the substrate. Since interference filters are known to the art, the details of the construction of the filters will not be discussed in detail here. The layers corresponding to two of the bands to be
30 blocked are shown at 121 and 123. It should be noted that the substrate does not need to be removed from the growth chamber during the deposition process, as the various layer compositions and thickness can be controlled by adjusting the precursor compositions and

deposition times used for each layer. Hence, the process is both economical and has a high yield.

Referring now to Figure 9, the pigment filters are then deposited on top of the band-
5 blocking filter layer using conventional photolithographic techniques. In this embodiment, pigment filters that transmit in the red, blue, and green are utilized. Exemplary pigment filters are shown at 131-133.

The above-described embodiments of the present invention utilize pigment filters to
10 provide the primary color filtration function and interference filters to adjust the edges of the pigment filter transmission curve to more nearly match a target transmission function. However, the present invention is not limited to this particular combination of filter types. In the more general case, any filter material that can be satisfactorily patterned can be utilized in place of the pigment filter. For example, pigment filters that utilize a colored photoresist may
15 be used. Similarly, any form of band blocking filter that can be constructed over one or more of the pigment filters can be utilized to alter the transmission curve of the pigment filter to more nearly match a target filter function. For example, band-pass filters based on other pigments can be utilized if the pigments do not have absorption bands that interfere with the operation of areas that utilize a different pigment.

Refer now to Figure 10, which is a cross-sectional view of another embodiment of a color sensor that utilizes a filter according to the present invention. While the above-described embodiments utilize trim filters that are deposited before the pigment filters, embodiments in which the trim filter is placed over the pigment filter can also be constructed.
25 When the trim filters are constructed from a material requiring deposition conditions that would damage the pigment filters, and the trim filters are to be deposited over the photodetectors, the trim filters must be applied first. However, embodiments in which the trim filter is constructed separately and then bonded or mounted over the pigment filters can also be constructed. Color sensor array 200 utilizes a trim filter layer 210 that is located over
30 the pigment filters 201-203 by applying a buffer layer 204 over the pigment filters and then bonding trim filter layer 210 to the buffer layer.

In addition, trim filter arrangements in which a portion of the trim filters is applied under the pigment filters and a second portion is applied over the pigment filters can also be advantageously used in certain circumstances. For example, the trim filter that removes the infrared may be useful in a number of different pigment filter arrangements. Hence, this filter could be incorporated over the photodiodes to provide a new starting substrate that can be used to construct a number of different color sensor arrays based on different pigment filters and/or trim filters. Such an underlying filter is shown at 212 in Figure 10.

While the ideal trim filter described above in Eq. (1) is preferred, other less ideal trim filters can be utilized and still provide significant advantages. In general, the present invention will provide an advantage if the combination of the trim and pigment filters is more nearly matched to the target filter function than the transmission curve of the pigment alone.

The above-described embodiments of the present invention have been described in terms of the CIE 1931 standard filters. However, the principles of the present invention can be applied to fabricate color sensor arrays for use with other filter standards. Furthermore, the number of pigment filters in the color sensor is not limited to three.

As noted above, the ideal trim filter utilizes a band-blocking filter that does not absorb light having wavelengths between the blocked bands. However, it should be noted that some absorption can be tolerated in these regions. If the transmission curve of the trim filter between the blocked bands is substantially constant, any absorption can be corrected by adjusting the gain of the photodetector associated with the color sensor in question.

The above-described embodiments of the present invention have been explained in terms of a color sensor array. However, a filter according to the present invention can be utilized in any application requiring a transmission filter whose transmission curve varies spatially.

Various modifications to the present invention will become apparent to those skilled in the art from the foregoing description and accompanying drawings. Accordingly, the present invention is to be limited solely by the scope of the following claims.